



Technical Data Sheet

DUMAKYD 85 72 D60

Long Oil Alkyd Resin

Primary Usages

VOC systems general purpose synthetic paint,
Varnish and liner binders for construction,
Wood and steel substrates

Packaging

Net 200 Kg in Steel Drum
Net 1.000 Kg in IBC
Bulk

Product Features

Low VOC,
Very good weathering resistance,
High colour durability and gloss retention,
Low viscosity,
High gloss, good acceptance of pigment,
Low odour

Technical Specifications

Test

Solid Content (%)
Viscosity (25°C, GHT)
Color (Gardner, 50%)
Acid Value (mg KOH/g)
Density (gr/cm³)

Range

84 - 86
7000 - 8000
Max. 6
Max. 8
0,95

Dilutability

Xylene	Complete
White Spirit	Complete
Toluene	Complete
n-Butanol	Limited

Composition

Oil Content	~ 72%
Type of Oil	Sunflower Oil Fatty Acid
Solvent Composition	D 60

Compatibility

Hydroxyl acrylic resins	Limited
Long oil alkyds	Complete
Short oil alkyds	Incompatible
Cellulose nitrate	Complete
Aliphatic polyisocyanate	Complete
Aromatic polyisocyanate	Complete
Amino resins	Complete

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Recommended Dryer Combinations

DUMADRY Co Octoate	0,05-0,07%
DUMADRY Zr Octoate	0,2-0,4%
DUMADRY Ca Octoate	0,1-0,3%

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.