



# DUMAN

## Technical Data Sheet

# DUMASET 735 F

## DCPD Based Flexible Putty Type Unsaturated Polyester Resin

### Primary Usages

Automotive body fillers,  
Patching and sealing compounds

### Packaging

Net 230 Kg in Steel Drum  
Net 1.100 Kg in IBC  
Bulk

### Product Features

Excellent flexibility,  
Easy sanding,  
Long shelf life,  
Special amine accelerator,  
Easily sticks to the galvanized,  
aluminum and polyester surfaces

### Technical Specifications

#### Test

Appearance  
Viscosity (25°C, cP)  
Styrene Content (%)  
Gel Time (min.) (25°C, 2.0% BPO)  
Density (gr/cm<sup>3</sup>)  
Shelf Life (month)

#### Range

Clear, Brownish  
500 - 600  
32 - 35  
9 - 10  
1,20  
6

### Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 6 months.

### Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.