



DUMAN

Technical Data Sheet

DUMASET 737 R

DCPD Based Rigid Putty Type Unsaturated Polyester Resin

Primary Usages

Automotive body fillers,
Patching and sealing compounds

Packaging

Net 230 Kg in Steel Drum
Net 1.100 Kg in IBC
Bulk

Product Features

Excellent hardness,
Fast sanding time even at cold temperatures,
Special amine accelerator,
Easily sticks to the galvanized,
aluminum and polyester surfaces

Technical Specifications

Test

Appearance
Viscosity (25°C, cP)
Styrene Content (%)
Gel Time (min.) (25°C, 2.0% BPO)
Density (gr/cm³)
Shelf Life (month)

Range

Clear, Brownish
350 - 450
33 - 37
9 - 10
1,20
6

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 6 months.

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.